

Dribond

Cemflex

Packaging



Mixing



Application



Uses



Substrates

New Concrete
Brick, Block
Cement Render
Building Boards
Compressed
Cement Sheet

One pack polymer modified rubber based tile adhesive

Description

A polymer modified rubber based, fast setting, cementitious adhesive for bonding ceramic and stone tiles to porous and non-porous surfaces.

Features

- Exceeds the requirements of AS4992
- Suitable for shower alcoves
- Ideal for new concrete floors subject to shrinkage cracks (0.4mm)

Uses

A thick or thin bed adhesive that can be used to fix porous and non-porous tiles internally and externally on floors and walls of concrete, cement render, screeds, brick and block. Apply internally to approved building boards (gypsum/ compressed cement sheet) and approved waterproofing membranes.

Performance Data

Meets the performance requirement of AS4992

Tensile Adhesion Strength

1.5MPa (28 days)

Coverage (Approximate) 20kg will cover 7-8m² using a 10mm notched trowel, over a true surface.

Specification

The ceramic tile adhesive will be a water resistant, fast setting, rubber based, polymer modified cement that conforms to AS4992 and has a minimum tensile adhesion strength of 1.5MPa such as **Cemflex** manufactured by Construction Chemicals and shall be applied in accordance with the manufacturer's application instructions.

Surface Preparation

The surface to be tiled must be firm and clean, free from dust, waxes, paint and other contaminants. Steel floated concrete floors must be mechanically roughened, washed thoroughly and allowed to dry prior to tiling. Prime with **Primax** on external and smooth surfaces and **Primebond** on internal porous surfaces.

Mixing

Mix with clean water using 3-4 litres per 10kg to a thick creamy consistency. Pot life is approximately 2 hours, depending on temperature. Allow to stand for 5-10 minutes and restir before use.

Set Time

Approximately 8-12 hours, depending on temperature, humidity and surface porosity. Allow longer for dense tiles.

Application

Apply with a notched trowel. For tiles 400x400 or greater use a 12mm notch and buttered tile back (as per the Australian standard AS3958). The final bed thickness must not be less than 2mm for walls and 3mm for floors, to accommodate movement. Spread about 1 metre at a time. Tiles must be set in place while the adhesive is still wet on the surface. Press tiles firmly into the adhesive using a slight twisting motion. Tiles must be firmly bedded into the adhesive so no voids occur beneath the tiles.

Do not spot fix.

Grouting

Grout after adhesive had set, approximately 8-12 hours. Use **Kemgrout** mixed with **Primebond**.

Precautions

Do not use in fully immersed applications (i.e. swimming pools). **Do not** use over timber floors.

Safety Precautions

Non-toxic but contains cement which contains silica. Wear gloves and appropriate respirator. Further information for this product is contained in the Material Safety Data Sheet. Refer; www.constructionchemicals.com.au

Shelf Life 1 year

**CONSTRUCTION
CHEMICALS**

www.constructionchemicals.com.au

● **ADELAIDE** PH: (08) 8243 7888
● **DARWIN** PH: (08) 89471811
● **PERTH** PH: (08) 9356 9999
● **AUCKLAND** PH: (09) 273 5444

● **BRISBANE** PH: (07) 3271 2944
● **MELBOURNE** PH: (03) 9761 4711
● **SYDNEY** PH: (02) 9756 3533
● **KUALA LUMPUR** PH: (603) 5122 2522

"The information contained in this technical publication is based on our current knowledge and experience and is provided as a guide only. In view of the many factors that may affect application it is the user's sole responsibility to ensure suitability for a specific purpose." 087 September 11

Downloaded from www.totalwaterproofingsupplies.com.au